


FIBER TYPE	STEEL FIBER WITH HOOKED ENDS
DIAMETER (mm)	1.00 ± 5%
LENGTH (mm)	50 ± 5%
ASPECT RATIO L/d	50
TENSILE STRENGTH OF DRAWN WIRE	1200 N/mm <sup>2</sup>
CROSS SECTION	ROUND

<b>MIXING</b>	SPAJIC steel fibers can be added during or after the batching of the concrete but should never be added as the first component. After adding all fibers, mix 1 min/m <sup>3</sup> concrete, not less than 5 minutes at full speed to ensure uniform distribution of the fibers through the concrete.
---------------	--

<b>DOSAGE</b>	The fiber dosages may vary depending on the type of application, concrete mix design and performance, and requirements of each particular project.
---------------	--

<b>DESCRIPTION</b>	SPAJIC steel fibers with hooked ends are produced from cold-drawn steel wire.
--------------------	---

<b>PACKING</b>	 <p>1000 kg per pallet 20 kg per paper bags Other pallets weights upon request</p>
----------------	---

<b>ADVANTAGES</b>	<ul style="list-style-type: none"> <li>Provides multi-dimensional reinforcement</li> <li>Improves impact resistance of concrete</li> <li>Enhances durability and toughness of concrete</li> <li>High resistance and good ductility</li> </ul>
-------------------	---

## SAFETY AND STORAGE

<b>APPLICATION</b>	<p>Shotcrete Jointless design Precast reinforcement Floor, tunnel Airport runways Ground supported slabs</p>
--------------------	--



USE PROTECTION ALL TIME

KEEP DRY DO NOT STACK

## CERTIFICATION



## THE BEST CHOICE FOR YOUR CONCRETE

Spajic D.O.O., Koroglaska 13, 19300 Negotin, Serbia

[www.spajic.com](http://www.spajic.com), [info@spajic.com](mailto:info@spajic.com)